

Specification

| Property | Unit | Value |
|---------------------------------------|-------------------|-------------------------------------|
| Density at 24°C | g/cm ³ | 1.63 |
| Viscosity at 24°C | cps | 13000 |
| Colour | ----- | Light Yellow |
| Shelf Life at Max 25°C in Darkness | Month | 12 |
| Base of Stone Adhesive | ----- | Polyester Resin |
| Base of Hardener | ----- | Dibenzoylperoxide Catalyst/BP-50 |

Cure Time

| Temperator (°C) | Gel Time (Min) | Cure Time (Min) | Hard Time (Min) (Ready to use) |
|-----------------|----------------|-----------------|-----------------------------------|
| 30 | 1.5 | 3 | 6 |
| 25 | 2 | 4 | 8 |
| 20 | 3 | 6 | 12 |

Mixed With 1% Hardener

All recommendations for use of our products, wether given by use in writing, verbally, or to be implied from the results of tests carried out bye us, are based on the current state of our knowledge. Notwithstanding any such recommendations the buyer shall remain responsible for satisfying himself that the product supplied by us are suitable for his intended process or purpose. Since we cannot control the application. use or processing of the products. we cannot accept responsibility therefore. We warrant that our products are free from defects in accordance with and subjects to our general conditions of supply.